



606-6 Lane Avenue North, Jacksonville, FL 32254
Phone (904) 693-8800 Fax (904) 693-8700

Product Data Sheet For:

PLEXICHIP

DESCRIPTION

- **PLEXICHIP SEAMLESS FLOORING** is a decorative, “poured in place” flooring system comprised of 1/4 or 1/8th inch decorative chips incorporated into PlexiGlaze No.4 or PlexiGlaze FLOOR FINISH. This system is typically top coated with PlexiCrest P or (for a super thicker top coat) PlexiCrest XP. PlexiChip systems are best used in or for commercial applications. PlexiChip floors provide a terrazzo- like appearance with the benefits of a seamless floor. These floors require no waxing and are easily cleaned. Long term care of PlexiChip floors can be done with renewed additional topcoats. Surface finish can be smooth or slip resistant.

RECOMMENDED USES

- Laboratories
- Traffic Aisles
- Restrooms
- Lobbies
- Concourse
- Pharmaceuticals
- Manufacturing areas such as offices and labs
- Halls/ Corridors
- Retail Stores
- Clean rooms
- Residential (Garages, Basements, Lanais, Kitchen floors, Balconies)

Benefits

- Easy installation
- Low odor
- Meets USDA, FDA, and OSHA standards
- Easy to use
- Good abrasion (wear) resistance
- Easy maintenance

Color

- PlexiChip is available in 1/4 or 1/8th inch decorative chips. The 1/4 inch chips are available in 10 standard blends. Color options include solid colors or custom multi-color pre-blends.

Limitations

- This product is best suited for application in temperatures between 55 and 95 degrees F. Substrate must be cleaned, sound and dry.

Surface Preparation

- This Product requires preparation in order to perform as expected. Substrate must be profiled clean sound and dry.

Installation Procedures

PlexiChip is applied with a roller or squeegee. A typical yield at 1/16th inch thickness is approximately 150-200 sq ft per gallon of epoxy and 1 pound of decorative chip per 9 sq ft. see the PlexiChip application instruction sheet for complete instructions.

PlexiChip

Technical Information

Cured film thickness	16 mils at 100 sq ft/ gallon spread rate
Salt spray Resistance, 25%	No effect after 100 hrs
Toxicity	Non- toxic, USDA approved

Physical Property	Test Method	Result
Hardness, shore D	ASTMD-2240	75-80
Water Absorption	ASTMD-570	.04%
Flammability	ASTMD-635	Self extinguishing
Tensile strength	ASTMD-638	12-13,000 PSI
Flexural Strength	ASTMD-790	18-19,000 PSI
Izod Impact	ASTMD-256	.50
Bonds strength to Concrete	ACI-403	Concrete fails before loss of Bond
Elevated temperature	MIL D-3134	No slip or flow
Thermal Shock, 50 cycles of immersion in chilled and boiling water	MIL F-52505	No cracking or loss of adhesion
UV resistance	MIL F 52505	No chalking or loss of adhesion
Abrasion resistance cs 10 wheel, wgt. Loss, 1000 gr. Load, 10000 cycles		30 mg

Before using any Plexi-Chemie Inc product be sure the Material Safety Data Sheet is read and understood.